

# Thermo Paint Spray 650°C

# **DESCRIPTION**

High quality heat-resistant black paint spray is used for treating parts exposed to high-temperature heating.

# **APPLICATION**

For coats of exhaust pipes and engines of cars and motorcycles as well as for chimneys and etc.

# **CHARACTERISTICS**

- · Fast drying at room temperature
- · Temperature resistance up to 650°C
- · Very good coverage
- · Good flow
- · High mechanical resistance
- · Good resistance to weather effects

#### **SUBSTRATES**

All kinds of metal surfaces.



Articles	Description	Pcs. / pack
4-151-0400	400 ml	6

# SUBSTRATE PRETREATMENT



- · Clean and degrease the surface with C.A.R.FIT Silicone Remover
- · Remove old coating and sand corrosion spots with grit P80 P240
- $\cdot$  Sand blast the surface
- · Again clean and degrease the surface with C.A.R.FIT Silicone Remover and thoroughly dry it

**APPLICATION** 



Shake thoroughly for at least 2 min



Apply 2 coats
Consumption: 1 spray can / ca. 1 – 1.2 m<sup>2</sup>



Flash-off between layers: 3 – 5 min





- · Spraying distance: 25 cm
- · Do not apply on chrome-plated surfaces
- $\cdot$  Apply at room temperature. Optimal application temperature: 15 25°C
- $\cdot$  Shake the spray can once more before application of each new coat
- $\cdot$  After use, hold aerosol can upside down and spray briefly to clean the nozzle
- $\cdot$  Maximum heat-resistance and fuel-resistance is achieved after stoving at 160 200°C for ca. 30 min

# **FURTHER TREATMENT**



Air drying / 20°C

· dust dry: ca. 10 min · dry to touch: ca. 15 min · can be exposed to high temperature: after ca. 1 h Drying time depends on environment temperature, humidity and coating thickness

# TECHNICAL DATA

Basis	silicone resin
Colour	black
Temperature resistance	up to 650°C

# STORAGE



This is a pressurized container, do not expose to direct sunlight or store above 35°C