

## Product information

# C.A.R. Fit Bitumen Underbody Protection

Site 1 / 2

Version 1 / 0921

### Product description

C.A.R. Fit Bitumen Underbody Protection is a durable corrosion protection based on wax/bitumen for floor pans, entry sections and wheel houses and so on. Excellent sound deadening properties, outstanding adhesion, elastic, non-sticking, high abrasion resistance and good resistance to de-icing salt.

### Color

black

### Hardener

--

### Mixing ratio

--

### Dilution

Ready to spray

### Spraying viscosity 4 mm DIN

--

### Application method

Application method	Pressure	Nozzle
Airless / Airmix	100 - 120 bar	0,33 - 0,5 mm
UBS spray gun	4 - 6 bar	5 - 10 mm

### Processing conditions

Ensure an adequate supply and exhaust air ventilation. Working temperature must be at least +10 °C. Max. air humidity 80 %.

Spraying operations	DFT	Consumption
1 - 2	500 - 100 µm	1 - 2 m <sup>2</sup> /l

### Flash-off time

#### Between the coatings

5 - 8 minutes

## Product information

# C.A.R. Fit Bitumen Underbody Protection

Site 2 / 2

Version 1 / 0921

### Drying

**Object temperature 20 °C**

Set to touch 2 - 4 hours

### Pot life at 20 °C

--

### VOC regulation

EU limit value: Category B/e 840 g/l

This product contains max. 840 g/l.

### Processing tips

After short shaking, spray the product uniformly in a criss-cross fashion on the substrate. By changing the air pressure and the spray distance to the object, the surface texture can be affected

The floor pan must be cleaned thoroughly. It must be dry, free from dust, grease, oil and rust.

Old non-adherent underbody coating must be removed.

Do not spray on engine, transmission, sump, cardan shaft, exhaust pipes, axles, springs, shock absorbers, brake cables, grease nipples etc., mask this parts before!