

Zinc Spray

DESCRIPTION

High quality zinc spray coating.

APPLICATION

The product is used for cold galvanizing of metal surfaces and as a primer for contact welding.

CHARACTERISTICS

- Fast drying at room temperature
- Good opacity
- Reliable protection against cathodic corrosion
- Good resistance to weather effects, petrol and chemicals
- Can be used as a weld through primer for contact welding

SUBSTRATES

Various metal surfaces.




Articles	Description	Pcs. / pack
4-399-0400	400 ml	6

SUBSTRATE PRETREATMENT



- Clean and degrease the surface with C.A.R.FIT Silicone Remover
- Remove old coating and sand corrosion spots with grit P80 – P240
- Again clean and degrease the surface with C.A.R.FIT Silicone Remover and thoroughly dry it

APPLICATION



Shake thoroughly for at least 2 min



Apply a few coats
Consumption: 1 spray can / 1.25 – 1.75 m²

Flash-off between layers: 3 – 5 min

- Spraying distance: 25 – 30 cm
- Apply at room temperature. Optimal application temperature: 15 – 25°C
- Shake the spray can once more before application of each new coat
- After use, hold aerosol can upside down and spray briefly to clean the nozzle

FURTHER TREATMENT



Air drying / 20°C
· dust dry: 10 – 15 min · dry to touch: 20 – 30 min · can be recoated after 24 h
Drying time depends on environment temperature, humidity and coating thickness

TECHNICAL DATA

Basis	epoxy resin, zinc
Colour	grey
Temperature resistance	up to 350°C

STORAGE



This is a pressurized container, do not expose to direct sunlight or store above 35°C